



Standard Guide for Evaluation of Coatings Applied to Plastics¹

This standard is issued under the fixed designation D 3002; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide is intended for the evaluation of clear and pigmented coatings designed for use on rigid or semirigid plastic substrates. Coated film and sheeting are not covered by this guide.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards²

- D 522 Test Methods for Mandrel Bend Test of Attached Organic Coatings
- D 523 Test Method for Specular Gloss
- D 658 Test Method for Abrasion Resistance of Organic Coatings by Air Blast Abrasive³
- D 822 Practice for Filtered Open-Flame Carbon-Arc Exposures of Paint and Related Coatings
- D 870 Practice for Testing Water Resistance of Coatings Using Water Immersion
- D 968 Test Methods for Abrasion Resistance of Organic Coatings by Falling Abrasive
- D 1308 Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes
- D 1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials
- D 2199 Test Method for Measurement of Plasticizer Migration From Vinyl Fabrics to Lacquers
- D 2244 Practice for Calculation of Color Tolerances and

Color Differences from Instrumentally Measured Color Coordinates

- D 2246 Method of Testing Finishes on Primed Metallic Substrates for Humidity-Thermal Cycle Cracking³
- D 2247 Practice for Testing Water Resistance of Coatings in 100 % Relative Humidity
- D 3170 Test Method for Chipping Resistance of Coatings
- D 3359 Test Methods for Measuring Adhesion by Tape Test
- D 3361 Practice for Unfiltered Open-Flame Carbon-Arc Exposures of Paint and Related Coatings
- D 3363 Test Method for Film Hardness by Pencil Test
- D 4060 Test Method for Abrasion Resistance of Organic Coatings by the Taber Abraser
- D 4141 Practice for Conducting Black Box and Solar Concentrating Exposures of Coatings
- D 4587 Practice for Fluorescent-UV-Condensation Exposures of Paint and Related Coatings
- D 5031 Practice for Enclosed Carbon-Arc Exposure Tests of Paint and Related Coatings
- D 5179 Test Method for Measuring Adhesion of Organic Coatings to Plastic Substrates by Direct Tensile Testing
- D 6695 Practice for Xenon-Arc Exposures of Paint and Related Coatings
- G 99 Test Method for Wear Testing with a Pin-on-Disk Apparatus

3. Significance and Use

3.1 This guide is designed to set up a series of screening tests that will indicate the performance level to be expected of a coating or coating system on a given plastic substrate.

3.2 Plastic substrates vary widely in their acceptance characteristics for a given coating.

NOTE 1—Not all tests apply to all plastics.

3.3 Surface cleaning or preparation prior to application of the coating can be critical to the proper performance of the coating.

4. Test Panels and Panel Preparation

4.1 Unless directed otherwise, conduct performance tests on coatings of specified thickness applied to a normally molded sample of the designated plastic.

¹ This guide is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.55 on Factory Applied Coatings on Preformed Products.

Current edition approved Nov. 1, 2007. Published November 2007. Originally approved in 1971. Last previous edition approved in 2007 as D 3002-01 (2007).

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn.

4.2 Preparation of test samples shall include any cleaning, metallizing, or priming operations agreed upon between the producer and the user.

4.3 Air-dry or bake the system according to the established schedule and aged as agreed upon between the producer and the user.

5. Effect on Substrates

5.1 Determine the physical properties of the substrate such as hardness, tensile strength, flexibility, or surface smoothness before and after applying the coating under test. Select the appropriate tests for the substrate from the appropriate volumes of the *Annual Book of ASTM Standards*.

6. Physical Properties—Coating Film⁴

6.1 Color:

6.1.1 *Pigmented (on Dry Film)*—Evaluate color differences visually in accordance with Practice **D 1729** and instrumentally in accordance with Practice **D 2244**.

6.2 Gloss:

6.2.1 Test in accordance with Test Method **D 523**.

6.3 Hardness:

6.3.1 Test in accordance with Test Method **D 3363** (determining film hardness using pencil test).

6.4 Adhesion:

6.4.1 Test in accordance with Test Methods **D 3359** for tape adhesion.

NOTE 2—Test Methods **D 3359** may be used to test the adhesion of organic coatings on plastic substrates. However, read Peel Adhesion Testing on Plastic Substrates in the Appendix Commentary at the end of Test Methods **D 3359** and Reference 7 for precautions to observe.

6.4.2 Test in accordance with Test Method **D 5179** direct for tensile adhesion.

6.5 Abrasion Resistance:

6.5.1 Test in accordance with Test Method **D 658** for air blast abrasion resistance.

6.5.2 Test in accordance with Test Methods **D 968** for falling (abrasive) resistance.

6.5.3 Test in accordance with Test Method **D 4060** for Taber abrasion resistance.

6.5.4 Test in accordance with Test Method **G 99** for Pin-on-Disk abrasion resistance.

6.6 Resistance to Chipping:

6.6.1 Test in accordance with Test Method **D 3170** for chipping resistance.

6.7 Flexibility and Elasticity:

6.7.1 Test in accordance with Test Methods **D 522** for mandrel bend flexibility.

⁴ In cases where alternate test methods (that is, A, B, C, etc.) are listed, use the appropriate test method for the application.

7. Durability/Environmental Properties⁴

7.1 Resistance to Plasticizer Migration:

7.1.1 Test in accordance with Test Method **D 2199** for plasticizer migration.

7.1.2 Time and temperature may be varied as agreed upon between the producer and the user.

7.1.3 If migration from a plastic substrate into a coating is being determined, the vinyl contact pad should be omitted.

7.2 Resistance to Temperature-Humidity Cycling:

7.2.1 Test in accordance with Method **D 2246** for humidity-thermal cycle cracking.

7.3 Humidity Resistance:

7.3.1 Test in accordance with Practice **D 2247** for humidity resistance.

7.4 Water Immersion:

7.4.1 Test in accordance with Practice **D 870** for water immersion resistance.

7.5 Resistance to Household Chemicals:

7.5.1 Test in accordance with Test Method **D 1308**.

7.6 Weather Resistance:

7.6.1 For outdoor exposure testing, expose in accordance with Practice **D 4141**. The type of exposure (Procedure A or Procedure B), duration of test and maximum acceptable appearance change shall be agreed upon between the producer and the user.

7.6.2 For accelerated weather testing, expose in accordance with either Practice **D 822**, **D 3361**, **D 4587**, **D 5031**, or **D 6695**. The practice to be used, duration of test and maximum acceptable appearance shall be agreed upon between the producer and the user. Because of differences in the spectral distributions of the exposure sources (xenon arc, fluorescent UV lamps, enclosed carbon arc and open flame carbon arc), as well as other conditions used in these types of laboratory weathering tests, these procedures may not result in the same performance ranking or types of failure modes of coatings, and different exposure durations may be required for detection of failure in the materials tested. Comparisons shall not be made of the relative stability of coatings exposed in the different types of apparatus.

8. Report

8.1 Report the appropriate results for each test as specified by the appropriate test method.

9. Precision

9.1 The precision of this guide is as specified in the individual test methods cited.

10. Keywords

10.1 coatings for plastics; plastic substrates

 **D 3002 – 07**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

现代环境
Modern Instruments

现代环境
Modern Instruments

现代环境
Modern Instruments

现代环境
Modern Instruments

现代环境
Modern Instruments